

High brightness two-component acrylic urethane paint for plastics

HAIUREX P

(UNP79- line)

Summary

HAIUREX P is the two-component acrylic paint with acrylic urethane resin and hardener of polyurethane resin.

This paint has special features such as anti-alcohol and chemicals, and highly adherence to many kinds of plastics. It is used for car interior parts, home appliances and cameras.

UNP79-line is one-coat metallic paint and has more brightness and gloss than NP79-line with same film performance.

Features

1. Higher gloss and brightness than NP79-.
2. Good workability.
3. Good material adhesion.
4. Good recoatability.

Paint number

UNP79- HAIUREX P each color

Recommended thinner & hardener

(Thinner)

ABS, PMMA

Z-27907 HAIUREX P THINNER(standard)

Z-27975 HAIUREX P THINNER(slow-dry)

PC/ABS, PC

Z-27970 HAIUREX P THINNER(standard)

Z-27993 HAIUREX P THINNER(slow-dry)

(Hardener)

Z-H-610(standard)

Applicable material

ABS, PC, PC/ABS, PMMA

Notice of use

1. Clean the substrate surface before spraying. Poor adhesion and craters may be caused by foreign objects, such as release agents, attached on the substrate.
2. Use the exclusive thinner for this paint. The film performance may decrease depending on the type of thinner.
3. Verify adhesion, solvent resistance of the substrate, hardening etc. before use, since a variety of resin grades have been developed.
4. Make sure to stir paint thoroughly before use. Pour the diluted paint into a stirred tank, and spray while stirring.
5. Store the paints in a cool (-20~40°C) and dark place, away from direct sunlight.
6. This paint is two-pack paint. Dilute minimal amount of this paint for use. Pot-life; period of time diluted paint remains suitable for use, of this paint is 4 hours at 20 degrees. Please note that quality of paint may decrease when applied after pot-life has expired.
7. Regarding further precautions, refer to MSDS etc.

Please send any questions to address included below

MUSASHI PAINT CO., LTD. SALES DEPT.

3rd floor, 2-30-16, Minami Ikebukuro, Toshima-ku, Tokyo, 171-0022, Japan

Tel. 81-3-3985-0634 Fax. 81-3-3971-1757

MUSASHI PAINT CO., LTD. OSAKA OFFICE

1-17-13, Mizuhai, Higashiosaka-shi, Osaka, 578-0921, Japan

Tel. 81-72-963-1133 Fax. 81-72-963-0606

MUSASHI PAINT CO., LTD. NAGOYA OFFICE

MinamikanA, Komakiharawell's21, 1758-1, Komakiharashinden, Komaki-shi, Aichi, 485-0012, Japan

Tel. 81-568-54-2113 Fax. 81-568-54-2117

MUSASHI PAINT CO., LTD. HIROSHIMA OFFICE

4-13 Taguchi research institutes, Higashi Hiroshima-shi, Hiroshima, 739-0038, Japan

Tel. 81-82-436-3423 Fax. 81-82-425-6316

MUSASHI PAINT INDUSTRY CO., LTD.

11-2, Kasumino, Sayamagahara, Iruma-shi, Saitama, 358-0032, Japan

Tel. 81-4-2934-4136 Fax. 81-4-2935-2736 (R&D dept.)

Tel. 81-4-2934-4138 Fax. 81-4-2935-2736 (Technical dept.)

High brightness two-component acrylic urethane paint for plastics

HAIUREX P

(UNP79- line)

Standard spray specifications		
Terms		Specifications
Mixing ratio Paint: Hardener: Thinner (by weight)		10:1:11±1
Spraying viscosity(IWATA VISCOMETER NK-2 at 20°C)		10±2 sec
Spraying method	Gun diameter	1.3±0.3mm φ
	Pressure of spray	0.3±0.1MPa
Distance of spray and material		25±5cm
Baking condition	Flash off	25°C × 5min.
	Baking	80°C × 30min.
Standard film thickness		15±5 μm

■ Coating performance

Test item	Test conditions	Result
Adhesion	Peeling of 1mm cross-cut adhesion tape(10 × 10)	100/100
Hardness	Mitsubishi pencil UNI 1kg of load	F~H
Eraser abrasion resistance	Sony eraser testing equipment, 1.64kgf, 100rounds	Pass
Alcohol resistance	99.5%ethanol, 500g/cm ² , 100rounds	Pass
Acid resistance	0.1N H ₂ SO ₄ , 5cc, 25°C × 24h	Pass
Alkali resistance	0.1N NaOH, 5cc, 55°C × 4h	Pass
Gasoline resistance	Regular gasoline, 30min,immersion	Pass
Heat resistance	Peeling of 1mm cross-cut adhesion tape after 85°C × 96h	100/100
Humidity resistance	Peeling of 1mm cross-cut adhesion tape after 50°C × 98%RH × 120h	100/100
Heat cycle resistance	Peeling of 1mm cross-cut adhesion tape -20°C × 3h ⇔ 60°C × 3h, 10cycle	100/100
Weatherability	SWOM, 300h, ΔE=1.0 less than	Pass
Painting condition	Material PC UNP79- HAIUREX P Silver Paint : Hardener (Z-H-610) : Thinner(Z-27970)=10 : 1 : 10(by weight) Flash off 25°C × 5min Baking 80°C × 30min(Seven days before examination start) Dry film 12 ± 2 μ m	
※The listed property value is not value of standard by our test result. Please adopt it after examining it enough		

November, 2013 JRD-UNP79-V.E1.1